

Polyken # 1600-HT

High Temperature Coating System



Market	Applications	Temperature Range
Oil, Gas or Water pipelines Pipeline Rehabilitation	Girthwelds for Water, Oil or Gas pipelines	up to 250°F (121°C)

System Description

The Polyken 1600-HT system is designed for the corrosion protection of new and existing pipelines with a maximum operating temperature of 250°F (121°C).

The products can be used for both buried and above ground applications, and the product is suitable to resist UV irradiation. The coating layer consists of a cross-linked polyethylene backing and a cross-linked elastomeric adhesive capable of maintaining

long-term protection at elevated temperature. The 1600 HT has a release liner to enable proper unwinding of the roll.

Product Advantages

- **Proven cross-linked backing formulation for long term temperature resistance and flexibility up to 248°F (120°C)**
Long-lasting performance.
- **User-friendly application to new or operating pipelines**
Save time and Money.
- **Manufactured at ISO certified Facility**
Reliability and Safety.

- **Shear Resistance at elevated temperature**
Provides high functional performance and safety.
- **High operating temperature rating**
Top performance in demanding conditions.
- **Plant or in-field application**
Flexible and conformable backing for easy plant or field application.

System Components

- **Primer layer #1619**
Percent solids: 20
Wt/ga: 7.4 lbs
Flash point: 45°F (7°C)
- **#1619**
Thickness: 25 and 30 mils
(0.635 and 0.762 mm)
Tensile strength: 40 lbs/in (7N/10mm)
Elongation: 500%

Product Construction

	1600-25HT	1600-30HT
• Backing	10 mils (0.25 mm)	10 mils (0.25 mm)
• Backing Color	Black or grey	Black or grey
• Adhesive	15 mils (0.38 mm)	20 mils (0.50 mm)

Product Properties - 50 mil System

	Test Method	Typical Value	
		English	Metric
Peel Adhesion to pipe	ASTM D1000 @ 23°C	24 lbs/in.	42 N/ 10 mm
Peel Adhesion to backing	ASTM D1000 @ 23°C	10.4 lbs/in.	18.2 N/ 10 mm
Shear Adhesion to Pipe	Modified Aleyeskey method 85°C 121°C	0.0014 in/hr.	1 x 10 ⁻⁸ m/sec
		0.0002 in/hr.	1.3 x 10 ⁻⁹ m/sec
Cathodic Disbondment	ASTM G8	0.4 in. radius	10 mm radius
Water Vapor Transmission Rate	ASTM E398 (100°F, 100% RH)	<0.01g/100 in. ² /24hr	<0.1g/m ² / 24hr
Impact Resistance	ASTM G14	27 in. lb	3.1 Joules
Penetration resistance	ASTM G17 21°C 121°C	40%	40%
		53%	53%
Volume resistivity	ASTM D257	10 ¹⁵ ohm•cm	10 ¹⁵ ohm•cm
Dielectrical strength	ASTM D149	40 kV	40 kV
Temperature range	Normal in-ground service	-30° to 250°F*	+34° to 121°C

* contact a Berry Plastics representative for specific project recommendations

Ordering Information

Polyken 1600-25HT and -30HT are available in roll form.

1600-25 HT BLK 2 X 100FT (4.1)

Core diameter	3.0" not indicated in the description (4.1 cm) only on request
Tape roll length	50 FT (on 2", 4", 6" wide), 100 FT (on 4", 6" wide), 200 FT (on 6" wide) and 400 FT (on 18" wide)
Tape width	2, 4, 6, 18"
Tape backing color	Black
Total tape thickness	1600-25HT (25 mils/0.635mm) & 1600-30HT (30 mils/0.762mm)

For other ordering options please contact your Berry Plastics representative.

Equation for Pipe Coating Requirements

$$\frac{\text{(Width of Coating in inches)} \times \text{(Area of pipe in square feet)}^*}{\text{(Width of Coating in inches - Overlap in inches)} \times 100} = \text{Squares}^{**} \text{ of Coating Required}$$

* Area of pipe in square feet = (Diameter in inches) / 12 x 3.1416 x (Length in ft)

** One Square = One hundred square feet = 9.29 square meters

$$\frac{\text{(Width of Coating in mm)} \times \text{(Area of pipe in square meter)}^*}{\text{(Width of Coating in mm - Overlap in mm)}} = \text{Square meters of Coating Required}$$

*Area of pipe in square meter = (Diameter in mm) /1000 x 3.1416 x (Length in meter)



CORROSION PROTECTION GROUP
www.berrycpg.com

Headquarters

Franklin, MA, USA
Tel: +1 508 918 1714
US Toll Free: +1 800 248 0149
Fax: +1 508 918 1910
CPG@berrypastics.com

Houston, TX, USA
Tel: +1 713 676 0085
US Toll Free: +1 888 676 7202
Fax: +1 713 676 0086
CPGH@berrypastics.com

Tijuana, Mexico
Tel USA +1 858 633 9797
Fax US: +1 858 633 9740
Tel Mexico: +52 664 647 4397
Fax Mexico: +52 664 607 9105
CPGTJ@berrypastics.com

Westerlo, Belgium
Tel. +32 14 722500
Fax +32 14 722570
CPGE@berrypastics.com

Baroda, India
Tel: +91 2667 264721
Fax: +91 2667 264724
CPGIN@berrypastics.com

The leading global partner in protecting the integrity of critical infrastructure.

Berry Plastics warrants that the product(s) represented within conform(s) to its/their chemical and physical description and is appropriate for the use as stated on the respective technical data sheet when used in compliance with Berry Plastics written instructions. Since many installation factors are beyond the control of Berry Plastics, the user is obligated to determine the suitability of the products for the intended use and assume all risks and liabilities in connection herewith. Berry Plastics liability is stated in the standard terms and conditions of sale. Berry Plastics makes no other warranty either expressed or implied. All information contained in the respective technical data sheet(s) should be used as a guide and is subject to change without notice. This document supersedes all previous revisions. Please see revision date on the right.

The information and values listed for Berry Plastics products are averages obtained from the relevant industry test procedures, carried out in our laboratories under controlled conditions. Values obtained on site will vary depending on the test methods and conditions. Manufacturing tolerances are available on request. Whilst Berry Plastics warrants its products to be free of material and manufacturing defects, Berry Plastics disclaims any liability in connection with the misuse of Berry Plastics products.

Local Distributor / Representative:

For contact details of local Distributors / Representatives
Please visit: www.berrycpg.com