

# Polyken Utility Tape



Market	Applications	Temperature Range	Performance
Oil, Gas or Water pipelines Refineries Wellhead, Gathering & Flow Lines	Oil/gas field applications for gathering & flow lines	up to 66°C (150°F)	AWWA C-209

## System Description

The Polyken utility tape coating systems have a rich tradition in the pipeline industry since their introduction in 1950. Designed specifically for the gas utility, oil field, and plumbing industries, the polyethylene backing and butyl rubber adhesive are highly conformable and remain flexible over a wide temperature range.

## Product Advantages

- **Established and proven performance**
- **Exceeds LT 1512-A, LT-0077, and MIL I-7798**
- **Conformable to irregular shapes specifications**
- **Hand or machine application**
- **Compatible with most generic plant coating systems**

## System Components

- **Max operating temperature**  
66°C (150°F)
- **Recommended primer**  
1027
- **Percent solids**  
30%
- **Wt/gal**  
7.3 lbs
- **Flash point**  
40°F

- **Also available**  
low VOC and zero VOC primer
- **Utility coating**  
Roll width: 1, 2, 4, 6 inch  
Roll length: 100 feet  
Colors: black, gray, yellow

DS-UtilityTape-REV8-AUG12-AARPS-0354

## System Products

### Polyken #900

General utility tape designed for small diameter pipe applications on elbows, fittings, field joints, and pipe sections. Highly conformable hand applied system for tight uniform protection on a wide variety of metal substrates.

### Polyken #910

All purpose field applied tape coating system for use in the oil patch and gas fields. Suited for hand application on a variety of steel structures common to the oil field. Frequently used for small makeshift repair and temporary corrosion protection behind protection diameter pipe gathering systems.

### Polyken #911 #908

General utility tape coating system for temporary makeshift repair of primary coating systems. Engineered for either hand or machine application,(only 911, not 908) the system is suited for the in-ground protection of joints, elbows, and tees.

### Polyken #920

General utility tape coating system to be used where higher mechanical protection is required. Designed for hand or machine application, the conformable polyethylene backing delivers a tough, uniform corrosion protection system.

## Product Properties

Properties	Test Method	Typical Value				
		#900	#908	#910	#911	#920
Total thickness	ASTM D1000	12 mils 0.30 mm	8 mils 0.20 mm	10 mils 0.25 mm	9 mils 0.23 mm	20 mils 0.51 mm
Backing thickness		8 mils	5 mils	6 mils	6 mils	15 mils
Adhesive thickness		4 mils	3 mils	4 mils	3 mils	5 mils
Tensile strength	ASTM D1000	25 lbs/in 44 N/10 mm	12 lbs/in 21 N/10 mm	18 lbs/in 32 N/10 mm	25 lbs/in 44 N/10 mm	35 lbs/in 61 N/10 mm
Elongation	ASTM D1000	175%	300%	250%	100%	250%
Peel adhesive to primed steel	ASTM D1000	← 100 oz/in 11 N/10 mm →				
Dielectric strength	ASTM D149	13 kV	7 kV	8 kV	13 kV	16 kV
Water vapor transmission rate	ASTM F1249 100°F, 100% RH	← 0.5 g/100 in <sup>2</sup> /24hr 0.8 g/100 cm <sup>2</sup> /24 hr →				
Holiday detection voltage	NACE RP-02-74	4.3 kV	3.5 kV	4.0 kV	3.8 kV	5.6 kV
Temperature range	Normal-in-ground service	← -30° to 150°F -34° to 66°C →				

DS-UtilityTape-REV8-AUG12-AARPS-0354



**CORROSION PROTECTION GROUP**  
www.berrycpg.com

### The leading global partner in protecting the integrity of critical infrastructure.

Berry Plastics warrants that the product(s) represented within conform(s) to its/their chemical and physical description and is appropriate for the use as stated on the respective technical data sheet when used in compliance with Berry Plastics written instructions. Since many installation factors are beyond the control of Berry Plastics, the user is obligated to determine the suitability of the products for the intended use and assume all risks and liabilities in connection herewith. Berry Plastics liability is stated in the standard terms and conditions of sale. Berry Plastics makes no other warranty either expressed or implied. All information contained in the respective technical data sheet(s) should be used as a guide and is subject to change without notice. This document supersedes all previous revisions. Please see revision date on the right.

The information and values listed for Berry Plastics products are averages obtained from the relevant industry test procedures, carried out in our laboratories under controlled conditions. Values obtained on site will vary depending on the test methods and conditions. Manufacturing tolerances are available on request. Whilst Berry Plastics warrants its products to be free of material and manufacturing defects, Berry Plastics disclaims any liability in connection with the misuse of Berry Plastics products.

Local Distributor / Representative:

For contact details of local Distributors / Representatives  
Please visit: [www.berrycpg.com](http://www.berrycpg.com)

#### Headquarters

**Franklin, MA, USA**  
Tel: +1 508 918 1714  
US Toll Free: +1 800 248 0149  
Fax: +1 508 918 1910  
CPG@berrypastics.com

**Houston, TX, USA**  
Tel: +1 713 676 0085  
US Toll Free: +1 888 676 7202  
Fax: +1 713 676 0086  
CPGH@berrypastics.com

**Tijuana, Mexico**  
Tel USA +1 858 633 9797  
Fax US: +1 858 633 9740  
Tel Mexico: +52 664 647 4397  
Fax Mexico: +52 664 607 9105  
CPGTJ@berrypastics.com

**Westerlo, Belgium**  
Tel: +32 14 722500  
Fax +32 14 722570  
CPGE@berrypastics.com

**Baroda, India**  
Tel: +91 2667 264721  
Fax: +91 2667 264724  
CPGIN@berrypastics.com