

Characteristics: S1137 is a high viscosity sealant based filler material delivered on rolls.

Applications: S1137 is used as a filler material with PERP and HTTE. Filler tape is used to fill the holiday thus restoring the mill applied coating thickness of the pipe.

Product description: S1137-XXXxYYYxZZZ

XXX = Width in mm
YYY = Thickness in mm
ZZZ = Length in mm

Material properties: Typical Softening point : 150°C
Typical Shear strength @ 23°C : 30 N/cm² @ 50 mm/min
Typical Peel strength @ 23°C : 55 N/cm @ 50 mm/min

Dimensions: Standard dimensions are:
Width: 50 mm / 2"
Thickness: 3 mm / 0.12"
Length per roll: 3000 mm / 12"

Product printing & Labelling: No printing.
The box in which S1117 is packed, is bearing a label mentioning:
Covalence Raychem Description
Covalence Raychem Part Number
Quantity
Spec. Code

Ordering info: S1137 is over packed in a box.
S1137-50x3x3000 (C6): 6 rolls per box.

For HTTE the S1137 filler is included in the kit.
For PERP the filler needs to be ordered separately.

Berry Plastics warrants that the product conforms to its chemical and physical description and is appropriate for the use stated on the technical data sheet when used in compliance with Berry Plastics written instructions. Since many installation factors are beyond the control of Berry Plastics, the user shall determine the suitability of the products for the intended use and assume all risks and liabilities in connection herewith. Berry Plastics liability is stated in the standard terms and conditions of sale. Berry Plastics makes no other warranty either expressed or implied. All information contained in this technical data sheet is to be used as a guide and is subject to change without notice. This technical data sheet supersedes all previous data sheets on this product.



Local Distributor / Representative:

For contact details of local Distributors / Representatives
Please visit www.berrycpg.com.

Headquarters : Berry Plastics Tapes & Coatings Division, Franklin MA, USA

Franklin, MA, USA
Tel: +1 508 918 1714
US Toll Free: +1 800 248 0149
Fax: +1 508 918 1910
CPG@berryplastics.com

Houston, TX, USA
Tel: +1 713 676 0085
US Toll Free: 01 888 676 7202
Fax: +1 713 676 0086
CPGH@berryplastics.com

Tijuana, Mexico
Tel USA 858 633 9797
Fax US: +858 633 9740
Tel Mexico: +52 664 647 4397
Fax Mexico: +52 664 647 4370
CPGTJ@berryplastics.com

Aarschot, Belgium
Tel: +32 16 55 36 00
Fax: +32 16 55 36 74
CPGE@berryplastics.com

Baroda, India
Tel: +91 2667 264721
Fax: +91 2667 264724
CPGIN@berryplastics.com